

Polyester film-based Laminate film


PET-L-F series

Outline

PET-L-F series is the laminate film to protect printed sheet.

Polyester film liner is used for increasing transparency. That makes printed sheet more clear after laminate.

Structure



Product Name	Tape Thickness (μm)	Base film (μm)
PET16-L-F	31	16
PET19-L-F	37	19
PET25-L-F	45	25
PET50-L-F	72	50

Properties

◆Adhesive strength (N/25mm)

	PET16-L-F	PET19-L-F	PET25-L-F	PET50-L-F
20min. *1	7.3	8.4	10.1	13.1
24Hrs. *2	14.1	15.2	17.8	20.1

*1:Peeling after 20 minutes

*2:Peeling after 24 hours

【Test method】

•JIS Z 0237 (2000) •Peel Speed 300mm/min •Substrate:Stainless steel (Polished with # 360)
•180° Peel •23°C•50%RH

Notices

Attach after wiping off oily, dusty and moisture substances on the surface of the adherend you may use.

Give an enough pressure when attaching, under the temperature condition over 10°C as possible.

Store it in a cool, dark place away from direct sunlight.

These data are representative so as not to guarantee for your conditions,nor do they for the wide range of each application described in this technical information.

Examining the compatibility of the adherend material with our product in advance, make a decision of starting to use.

Such as know-hows contained in this document, trade secrets, copyrights, and patents,each of all intellectual property's rights belongs only to our company.

Any copies, reprints, reproductions and disclosing any part of this document to a third party are prohibited without our prior approval.

All information and data in here should be used as a guide.

They do not constitute a warranty of any kind by NEION Film Coatings Corp.